

<b>Vertical Flammability Test Results (60-s)</b>			<b>TR# 1130</b>		
<b>Regulation:</b>	14 CFR 25.853(a)	<b>Criteria:</b>	Appendix F, Part I(a)(1)(i)	<b>Procedure:</b>	Appendix F, Part I(b)(4)

Customer Information
Electro-LuminX Lighting 1320 N. Boulevard Richmond, VA 23230

Sample Notes
Manufacturer: Honeywell Part Number: PS4000N

Conditioning: 24 hours minimum at 70 ± 5 °F and 50 ± 5 %RH.	Flame Temp: 1,550 °F minimum
---	------------------------------

Sample	Ignition Time (sec)	Flame Time (sec)	Drip Flame Time (sec)	Burn Length (inch)
1	60.0	0.0	0.0 No Drips	4.4
2	60.0	0.0	0.0 No Drips	4.8
3	60.0	0.0	0.0 No Drips	5.0
<b>Average:</b>		<b>0.0</b>	<b>0.0</b>	<b>4.7</b>
Result:		PASS	PASS	PASS

Acceptance Criteria:
Flame Time Average: 15.0 seconds maximum Drip Flame Time Average: 3.0 seconds maximum Burn Length Average: 6.0 inches maximum

Test Comments:
All samples self-extinguished around 40 seconds into the test.

Results	
<input checked="" type="checkbox"/> <b>PASS</b>	<b>Deviations:</b> None
<input type="checkbox"/> <b>FAIL</b>	<b>Result Notes:</b> None

The results of this test report have been obtained in compliance with the applicable requirements and/or specifications. The test results relate only to the items tested.

*Andrew Feghali*  
 Andrew Feghali, Lab Manager

4/28/2017